









Product properties			
Format	1170 x 120 x 13 mm	2200 x 185 x 13 mm	2380 x 233 x 13 mm
Top layer	≥ 2.5 mm		
Packaging	Pack	12 Elements 1,685 m ² / 11,532 kg	9 Elements 3.663 m ² / 26.163 kg
	Pallet	30 Packs 50,544 m ² / 345,96 kg	32 Packs 117,216 m ² / 837,216 kg
Guarantee (according to Parador guarantee conditions)		25 years (domestic area)	
Notes		- cleaning and maintenance see instructions - technical changes reserved	

Product labelling			
 EN 14342:2013		 www.blauer-engel.de/uz176	
			

Tolerances (EN 13489)	
Admissible difference in length (± 0.1 %)	± 0.05 %
Admissible difference in width (± 0.2 mm)	± 0.1 mm
Squareness of the element (≤ 0.2 %)	≤ 0.05 %
Longitudinal curvature along the element (≤ 0.1 %)	≤ 0.05 %
Transverse curvature across the width (≤ 0.2 %)	≤ 0.08 %
Height differences of elements (≤ 0.2 mm)	≤ 0.18 mm
Moisture content at the time of first delivery (5-9%)	6 - 8 %

Classification general product features			
		Test method	Rating
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
	Effect of a furniture leg	EN 424	No visible changes
	Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN ISO 10456	0.087 m ² *K/W
	Formaldehyde (E1 = 0.1 ppm)	EN 717-1	≤ 0.05 ppm
	Acoustical - Impact noise reduction	ISO 717-2	18 dB (with Akustik-Protect 100)
	Disposal		EAK-Code-number 20 01 38

Classification surface characteristics				
		Test method	Rating	
			Lacquer	Natural oiled plus
	Slip resistance	EN 13893	μ ≥ 0.47	μ ≥ 0.49
		CEN/TS 15676	29 SRT (SRV wet) 51 SRT (SRV dry)	99 (USRV)
	Reaction to fire, click-installation as a floating floor	EN 13501-1	D _{fl} s1	
	Reaction to fire, installation by all-over adhesion	EN 13501-1	D _{fl} s1	
	Chemical resistance	EN 13442	Category 5	Category 5 excepting ammonia solution (cat. 2)
	Bond strength / Cross cutting test	ISO 2409	0	n.n.
	Slip resistance, inclined plane	DIN 51130	R 9	R 10

Changed:	QMB	File name:	PA_TDS_Parkett_Classic-3025_EN_20210501
Date:	01.08.2013	Latest update at:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.05.2021

Free sorting according to EN 13489		
Assortment:	Wide plank / Extra-sized wideplank	
Characteristics according to EN 1310:	Upper side of the plank	
Type of wood:	Oak	
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE	
Shortcut / grade / date (internal):	ER-LH-EI-N3	ER-LH-EI-N6-N7
	Version 3 2019	Version 10 2019
	N3	N7
Grade:	Classic	Rustique
Sound sapwood	not permitted	permitted
Knot (intergrown)	permitted: up to 30 mm	permitted: up to 80 mm
Falling out knot	permitted: up to 25 mm	permitted: up to 60 mm
Pinkknots	permitted: cluster of knots	
Filling	permitted	
Slight cracks / hairline cracks	permitted	
Sugar inclusions, mineral inclusions	-	
Bark pocket	not permitted	permitted
Lightning cracks	permitted	
Slope of grain	no criterion	
Healthy heart	permitted	
Medullary ray	permitted	
Discoloration, colour variation	permitted: slight colour variations	permitted: all colours
White streaks	permitted	
Pilling sticks marking	not permitted	
Biodeterioration (EN 1311)	not permitted	
Non-visible parts		
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.		
Comment		
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.		

Changed:	QMB	File name:	PA_TDS_Parkett_Classic-3025_Anhang_EN_20210501
Date:	01.08.2013	Update:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.05.2021
			Page 1 of 2

Free sorting according to EN 13489		
Assortment:	Wide strip	
Characteristics according to EN 1310:	Upper side of the plank	
Type of wood:	Oak	
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE	
Shortcut / grade / date (internal):	ER-TT0-EI-N1/A2/A4	ER-TT0-EI-N1/A2/A4
	Version 2 2018	Version 2 2018
	A2	A4
Grade:	Natur	Living
Sound sapwood	not permitted	permitted
Knot (intergrown)	permitted: up to 15 mm	permitted: up to 35 mm
Falling out knot	not permitted	permitted: up to 15 mm
Pinkknots	permitted: cluster of knots	
Filling	permitted	
Slight cracks / hairline cracks	not permitted	permitted
Sugar inclusions, mineral inclusions	-	
Bark pocket	not permitted	
Lightning cracks	not permitted	
Slope of grain	no criterion	
Healthy heart	not permitted	
Medullary ray	permitted	
Discoloration, colour variation	permitted: slight colour variations	
White streaks	-	
Pilling sticks marking	not permitted	
Biodeterioration (EN 1311)	not permitted	
Non-visible parts		
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.		
Comment		
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.		

Changed:	QMB	File name:	PA_TDS_Parkett_Classic-3025_Anhang_EN_20210501
Date:	01.08.2013	Update:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.05.2021
			Page 2 of 2