

Product quality		Tolerances (EN 13329)	
Formats	858 x 143 x 8 mm	Squareness of the elements (≤ 0.50 mm)	≤ 0,10mm
Packaging	Pack: 13 elements / 1.595 m ² / 12.13 kg	Determination of Linearity (≤ 0.30 mm)	≤ 0,10 mm/m
	Pallet: 56 packs / 89.32 m ² / 694.32 kg	Block alignment	± 2 mm
Guarantee (according Parador guarantee conditions)	Domestic area	Surface flushness	(average ≤ 0.15 mm)
	Commercial area		(max. ≤ 0.15 mm)
Notes	Lifetime 10 years - not suitable for all-over adhesion - min. compressive strength of underlay (CS) ≥ 120 kPa (e.g. Akustik-Protect) - cleaning and maintenance see instructions - technical changes reserved	Opening between installed elements	(average ≤ 0.15 mm) (max. ≤ 0.20 mm)
		Flatness of elements	fw, concave ≤ 0,15 % fw, convex ≤ 0,20 %
			fl, concave ≤ 0,50 % fl, convex ≤ 1,00 %



Classification		
	Test method	Rating
Utility class 23 domestic areas with intensive use	EN 13329	Living room, hall, kitchen, home office
Utility class 32 commercial areas with medium use	EN 13329	Classrooms, small offices, shops
Abrasion	EN 13329, Annex E	AC 4 (≥ 4.000 rev.)
Impact resistance (small / big ball)	EN 13329, Annex H	≥ 12 N / ≥ 750mm
Reaction to fire	EN 13501-1	C _f s1
Slip resistance	EN 13893	μ ≥ 0,35
	EN 14041	DS
Staining resistance	EN 438-2	Category 1+2: level 5 Category 3: level 4/5
	EN 438-2	level 4
Cigarette resistance	EN 438-2	level 4
Light fastness	EN ISO 4892-2	Grey scale: Stage ≥ 4
Resistance to roller castor chairs	EN 425	Type W, no visible changes
Electrical behaviour	EN 1815	≤ 2 kV
Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN 12664	0,048 m ² *K/W
Moving a furniture leg	EN 424	No visible changes
Indentation-residual	ISO 24343-1	≤ 0,05mm
E1 Formaldehyde emission (E1 = 0.1 ppm)	EN 16516	≤ 0,05 ppm
Locking strength of mechanically assembled panels	ISO 24334	> 1 kN/m (long side) * kN/m (short side)* not reportable due to construction
Acoustical - Impact noise reduction	ISO 717-2	14 dB (on Akustik-Protect 100)
Dimensional stability	EN 13329, Annex C	≤ 0,9mm
Thickness swelling	ISO 24336 (≤ 18 %)	≤ 12 %
Surface soundness	EN 13329, Annex D	≥ 1,8 N/mm ²
Scratch resistance	EN 438	Level 4
Slip resistance on an inclined plane	DIN 51130	Rustique texture: - / Other: R9
Disposal		EAK-Code-number 20 01 38
Damp room suitability: "The water-resistant product structure enables use in damp rooms (with up to 1h protection against standing water. Please observe installation instructions).		

Changed:	QMB Parador	File:	PA_TDS_Laminat_Trendtime-3_EN_20210201
Date:	01.01.2014	Latest update at:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.02.2021